

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
15 April 2004 (15.04.2004)


PCT

(10) International Publication Number
WO 2004/031292 A2

- (51) International Patent Classification⁷: **C08L 23/04**, 101/00, 53/02 // (C08L 23/04, 101/02) (C08L 101/00, 23:04)
- (21) International Application Number: PCT/US2003/030434
- (22) International Filing Date: 26 September 2003 (26.09.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data: 60/415,639 2 October 2002 (02.10.2002) US
- (63) Related by continuation (CON) or continuation-in-part (CIP) to earlier application: US 60/415,639 (CIP) Filed on 2 October 2002 (02.10.2002)
- (71) Applicant (for all designated States except US): **DOW GLOBAL TECHNOLOGIES INC.** [US/US]; Washington Street, 1790 Building, Midland, MI 48674 (US).
- (72) Inventors; and
(75) Inventors/Applicants (for US only): **YALVAC, Selim** [US/US]; 210 Teakwood, Lake Jackson, TX 77566 (US). **KARJALA, Teresa** [US/US]; 56 Mandevilla Court, Lake Jackson, TX 77566 (US). **CHEUNG, Yunwa, W.** [US/US]; 104 Rosemary Lane, Lake Jackson, TX 77566 (US). **MONCLA, Brad** [US/US]; 56 Nandina Court, Lake Jackson, TX 77566 (US). **WALTHER, Brian, W.** [US/US]; 630 Highway 332, Lake Jackson, TX 77566 (US).
- (74) Agent: **SPENCER, Lee**; The Dow Chemical Company, Intellectual Property, B-1211, 2301 N. Brazosport Boulevard, Freeport, TX 77541 (US).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, YU, ZA, ZM, ZW.

[Continued on next page]

(54) Title: POLYMER COMPOSITIONS COMPRISING A LOW VISCOSITY, HOMOGENEOUSLY BRANCHED ETHYLENE/ α -OLEFIN EXTENDER



(57) Abstract: A thermoplastic composition is described that comprises (i) from 1 to 99 percent by weight of the total composition of at least one thermoplastic copolymer, for example, styrene block copolymers, and (ii) from 1 to 99 percent by weight of the total composition of at least one homogeneously branched ethylene/ α -olefin interpolymers, for example ethylene/1-octene, having a density of less than or equal to 0.899 g/cc and a Brookfield viscosity of greater than 500 cP (350°F).